



Morricite WB Epoxy Garage Floor

DESCRIPTION

Morricite Water-based Epoxy Garage Floor Coating is a two component, ambient-cure waterborne epoxy floor coating designed for superior concrete garage floor resistance to hot tire pick-use plus convenience to the consumer.

ADVANTAGES

- Easy to apply
- Wear and abrasion resistance
- Good adhesion to damp concrete
- Low odor, Non-flammable, non toxic paint
- Resists damage by gasoline, antifreeze, motor oil, salt, and hot tires.

TYPICAL USE

- Garage Floors
- Basement Floors
- Driveways
- Walls

TYPICAL PHYSICAL PROPORTION @75°F (23°C)

Mixing ratio 3:1 Base to Activator by Volume. Submitted in 1-unit kits

Film thickness: Wet Film 6.0 to 7.0 mils

Dry film 3.0 to 3.5 mils

Theoretical Coverage:

@1 mil DFT (25u) 800-850 ft²/gal

1-Unit kits coverage 250 ft²/gal

Working Time:

@50 % Humidity	2hrs. (varies with temperature)
Cure Time:	Foot traffic 24 hours Vehicle traffic 3-5 days
Flash Point:	> 200°F (93°C) Activated material
Shelf Life:	2-3 years (Unopened container)

SURFACE PREPARATION

The substrate must be clean (free of dirt, dust, paint, grease, oil, rust and other contaminants), sound and durable. New concrete must be fully cured (28 days minimum) and all laitance and curing compounds removed. Suitable preparation methods include grit blasting and scarification. The recommended minimum pull-off strength of the prepared substrate is 200 psi.

SAFETY

For industrial and professional use **ONLY**.

For detailed safety guidelines, please refer to the Safety Data Sheet (SDS)

WARRANTY INFORMATION

Values stated herein are typical values based on periodic testing and product experience. MTT DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING WITHOUT LIMITATION THOSE OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. Where customer demonstrates non-conformance of product to typical values stated herein, MTT will, supply replacement product or, at its discretion, credit customer's account for the purchase price of non-conforming product. Recommendations herein as to the surface preparation, application, maintenance, and other matters involving storage, handling, or use of product are based on the best information available. Because MTT has no control over such matters, or over substrate or other conditions that may affect ultimate performance, customer has the obligation to determine suitability of product for the intended purpose. MTT SHALL HAVE NO RESPONSIBILITY FOR ANY CONSEQUENTIAL, INCIDENTAL, SPECIAL, EXEMPLARY OR PUNITIVE DAMAGES BUT ONLY FOR THE REPLACEMENT OR CREDIT MENTIONED ABOVE. All claims for replacement or credit must be made within one year from date of shipment. The sale and purchase of product from MTT are subject in each case to MTT's terms and conditions of purchase.

215.949.1474 / Fax 215.949.9422 / Email:office@masterterrazzo.com