



## Morricite WB Polyurethane Satin

### DESCRIPTION

Morricite WB 1041 is a two component aliphatic polyurethane floor coating and Sealer available in a low gloss, clear and/or tinted that provides the properties and performance characteristics of solvent based systems. It is a unique, environmental friendly with the ease of application associated with water-based systems.

### ADVANTAGES

- Water-based
- Gloss finish
- Ultra Low Voc Levels (<10g/L)
- UV stable
- Great penetration and bond strength
- Good abrasion, impact and wear resistant
- Good chemical resistance

- Resists common acids, fuel grease, salt and skydrol

### TYPICAL USES

- Clear sealer over Terrazzo and Concrete
- Showroom floors
- Retail store floors
- Pharmaceutical facilities
- Air craft hangars
- Commercial and industrial flooring top coat

### TYPICAL PHYSICAL PROPERTIES

Mix Ratio A:B	2 to 1 by volume
Pot Life:	2 ½ hours approx.
Spreading Rate per Coat:	
Wet mils thickness	4.0 to 6 mils
Dry to touch	5-6 hours approx. @23°C/50%RH
Initial Cure	24 hrs. Minimum
Final Cure	7 days
VOC lbs/gal (g/L) (EPA method 24):	<10 g/l
Finish (60°Gloss)	85-90
Pencil Hardness	
ASTM D 3363	4H
Taber abrasion, mg loss	
CS-17 wheel, 1,000 cycles ASTM D 4060	45 mg Loss

---

## SURFACE PREPARATION

The substrate must be clean (free of dirt, dust, paint, oil, rust and other contaminants), sound and durable. New concrete must be fully cured (28 days minimum) and all laitance and curing compounds removed. Suitable preparation methods include grit blasting and scarification. The recommended minimum pull-off strength of the prepared substrate is 200psi.

## APPLICATION

### DO NOT ALLOW TO FREEZE

Install Morricite 1040 at a substrate temperature of 50°F (10°C) to 85°F (30°C). Mix two parts A and one part B (2:1) by volume with a slow speed drill and Jiffy blade for three minutes and until uniform. Apply 1040 with ¼" nap roller. Use small chip brushes along the perimeter and in other difficult to reach areas. Morricite 1040 can be dry to the touch in 5 to 6 hours after application depending on ambient temperature, slab temperature and humidity. Allow 24 hours minimum for wheeled traffic and water exposure.

NOTE: 1040 tacks quickly, you must maintain a wet edge to avoid the potential for roller lines, if you see lines during application cross roll to eliminate.

1040 cure(s) to a very hard, glass-like film, recoating after cure is difficult. If a second coat is required or planned the second coat 2-4 hrs after installation of the first coat. On a floor this will require spiked shoes, the film will still be tacky and care will need to be taken to roll out any cleat marks. If the first coat has cures overnight it will require sanding and the application of an epoxy primer, contact Technical Services.

## COVERAGE

Concrete surfaces 4-6 mils.                      250-400 ft<sup>2</sup>/gallon.  
Coverage will vary depending on substrate profile and porosity.

## CLEANUP

Use Xylene or MEK. Do not use alcohol.

## SAFETY

For industrial and professional use **ONLY**.

For detailed safety guidelines, please refer to the product Safety Data Sheet (SDS).

## WARRANTY INFORMATION

Values stated herein are typical values based on periodic testing and product experience. MTT DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING WITHOUT LIMITATION THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Where customer demonstrates non-conformance of product to typical values stated herein, MTT will supply replacement product or, at its option, credit Customer's account for the purchase price of non-conforming product. Recommendations herein as to the surface preparation, application, maintenance, and other matters involved in storage, handling, or use of product are based on best information reasonably available to MTT. Because MTT has no control over such matters, or over substrate or other conditions that may affect ultimate performance, Customer has the obligation to determine suitability of product for the intended purpose, and MTT SHALL HAVE NO RESPONSIBILITY FOR ANY CONSEQUENTIAL, INCIDENTAL, SPECIAL, EXEMPLARY OR PUNITIVE DAMAGES BUT ONLY FOR THE REPLACEMENT OR CREDITING REMEDY ABOVE. All claims for replacement or crediting must be made within one year from date of shipment. The sale and purchase of product from MTT are subject in each case to MTT's Terms and Conditions of Purchase.

---

Master Terrazzo Technologies / PO Box 226 / Bristol, PA 19007  
8000 Bristol Pike / Levittown, PA 10957 / [www.masterterrazzo.com](http://www.masterterrazzo.com)  
215.949.1474 / Fax 215.949.9422 / Email: [office@masterterrazzo.com](mailto:office@masterterrazzo.com)